

Northfoam®

Material Characteristics

Closed cell polyethylene foam

Density 33, 140 and 170 Kg/m³

Northfoam® 33 is a lightweight padding material

Applications

Prosthetic Socket Liner
Foot Insoles

Sheet size:

Northfoam® 140 & 170

- 950 x 950mm

Northfoam® 33 -

Roll form 1m wide

Available in the following thickness:

Northfoam® 140 & 170 -

2mm through to 35mm

Northfoam® 33

- 3mm, 4mm and 6mm

Available in the following colours:

Northfoam® 140 & 170 - Flesh

Northfoam® 33 - White

Moulding temperature:

Northfoam® 140 & 170 -

120°C - 150°C / 266°F - 302°F

Northfoam® 33 - 120°C / 248°F

Cooking time:

3 minutes per mm thickness

N.B. As all ovens have slightly different heating characteristics please use our recommended timings as a guide only.



Northfoam 140
is available with
SilverShield®



**NORTH SEA
PLASTICS**

www.northseaplastics.com